

BEST AVAILABLE COPY**I. AMENDMENTS TO THE CLAIMS**

Please entered the amendments specified below into the file of this Application. A complete listing of all claims in the Application is provided below along with each claim's status, which is indicated in a parenthetical expression after each claim number. For claim amendments, deleted matter is indicated by strike-out text and added matter is indicated by underlined text.

1-8 (canceled).

9. (currently amended) A method of making a supercapacitor structure comprising positive and negative electrodes, a porous separator membrane and an electrolyte solution comprising the steps of:

laminating an activated carbon fabric, comprising an active surface area in the range of 1,500 m²/g. to an electrically conductive positive current collector foil to produce a porous positive electrode subassembly;

laminating an activated carbon fabric, comprising an active surface area in the range of 1,500 m²/g. to an electrically conductive negative current collector foil to produce a porous negative electrode subassembly;

disposing the porous separator membrane between the carbon fabric surfaces of the electrode subassemblies to form an assembly;

heating the assembly under pressure to form a porous laminated assembly; and
contacting the porous laminated assembly with electrolyte.

10. (previously presented) The method of claim 9 wherein heating the assembly under pressure comprises heating to temperature in the range 120° to 160° C under pressure.

11. (previously presented) The method of claim 9 wherein heating the assembly under pressure comprises heating under a pressure in the range 3×10^4 to 5×10^4 Pa.

12. (previously presented) The method of claim 9 wherein the assembly is heated under pressure by heated calendar rolling.

13. (previously presented) The method of claim 9 wherein the contacting the assembly with electrolyte comprises contacting the assembly with a non-aqueous electrolyte solution.

14. (previously added) The method of claim 9 wherein the porous separator membrane comprises an ultra-high molecular weight micro-fibrillar polyolefin.

15. (previously presented) The method of claim 9 wherein the porous separator membrane comprises a polyethylene fabric with a micro-fibullar structure and a sufficiently high molecular weight that the polyethylene fabric maintains porosity after being heated to surface temperatures in a melting point range of the polyethylene fabric.

16. (previously presented) The method of claim 9 wherein the positive current collector foil comprises an open mesh aluminum grid.

17. (previously added) The method of claim 9 wherein the negative current collector foil comprises an open mesh copper grid.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.